

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : D06M 14/00, 14/02, 14/08, 14/16, 23/00	A1	(11) International Publication Number: WO 97/13024 (43) International Publication Date: 10 April 1997 (10.04.97)
(21) International Application Number: PCT/GB96/02220 (22) International Filing Date: 9 September 1996 (09.09.96) (30) Priority Data: 9519824.8 29 September 1995 (29.09.95) GB (71) Applicant (for all designated States except US): THE SECRETARY OF STATE FOR DEFENCE [GB/GB]; Defence Evaluation & Research Agency, DRA Farnborough, Hampshire GU14 6TD (GB). (72) Inventors; and (75) Inventors/Applicants (for US only): WILLIS, Colin, Robert [GB/GB]; CBDE, Porton Down, Salisbury, Wiltshire SP4 0JQ (GB). BREWER, Stuart, Anson [GB/GB]; CBDE, Porton Down, Salisbury, Wiltshire SP4 0JQ (GB). (74) Agent: SKELTON, Stephen, Richard; D/IPR (DERA) Formalities, Poplar 2, MOD (PE) Abbey Wood #19, P.O. Box 702, Bristol BS12 7DU (GB).		(81) Designated States: GB, JP, US, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: FIBRE REACTIVE POLYMERS (57) Abstract A group of polymers for treatment of cellulose based materials which are characterised by a functional group which binds the polymer to the material. This allows treatment of, for example cotton based fabrics, to improve, for example, their oil and water repellent properties.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

FIBRE REACTIVE POLYMERS.

The present invention relates to a group of polymers suitable for binding to cellulose or woollen based material and is useful for the treatment of cloth, linen fabric and the like.

The durability of certain functional treatments (e.g. water or oil repellency) on cellulose based fabrics can be improved by the addition of cross-linkable resins to their formulations. Depending on the type of resin employed, fixation to the cloth may occur under acidic conditions (eg with dimethyloldihydroxyethylene urea) or under neutral conditions (eg with a blocked polyisocyanate).









The use of certain groups, for example triazines, to bind molecules to cellulose based, and other, materials is known from the chemistry of reactive dyes. For example, the 2,4-dichloro-6-aminotriazyl group is used to bind a family of dyes, known commercially as Procion dyes, to cellulose materials (see for example, The Chemistry of Synthetic Dyes, Vol. IV - Reactive Dyes, K Venkataraman Ed., Academic Press.).

The use of fluoroalkyl compounds to improve the oil and water repellency of articles is described, for example, in GB 1,102,903. These compounds are non-polymeric and the invention described therein requires the use of organic solvents whereas the current invention may be carried out in aqueous solvents.

Whilst resin treatments can improve the durability of certain finishes and impart dimensional stability and durable press properties to fabrics, the acid catalysts required to bring about the cross-linking reactions can damage acid sensitive cloth such as cotton. Moreover, excessive cross-linking can also lead to a reduction in abrasion resistance (see for example Textile Chemist and Colorist, 1995, Vol. 27, page 17, R J Harper and Melliand Textilber., 1986, Vol. 67, p.E61-5, J. Hearle). Problems also arise with resins that contain formaldehyde and this has prompted considerable research into the development of cross linking agents that do not contain this compound (see for example Textile Res. J., 1994, Vol.64, page247, N. R. Bertoniere et al).

According to this invention, a polymer for the treatment of materials is characterised by a plurality of side groups of general formula -A-Az, where:

A = (CH₂)_n, wherein non adjacent CH₂ groups may be replaced by O, CO₂, OCO
OCO₂, or phenylene and n may have any integral value from 0 to 16,
and Az is selected from:



and




where X_1, X_2 etc are independently selected from halogen, -NHR, -SO₂CH₃, Alkyl, Aryl, -O-Alkyl or -O-Aryl and at least one of X_1, X_2 etc per group Az is halogen:

$Y = -NH-, -NR- (R=Alkyl), -NHCO-, -O-,$ or $-S-$ and

$Z = -SO_2NH-$ or $-SO_2-$


In a preferred embodiment, the polymer also contains fluorine bearing side groups.

In a further preferred embodiment, the polymer also contains side groups bearing R_f where:



In a further preferred embodiment, the polymer contains the side group -CO₂ R_f .

In a further preferred embodiment the polymer has the repeat unit:



According to a second aspect of the invention, a material is provided with improved physical properties by virtue of treatment of said material with the polymer of the first aspect of the invention.

According to a third aspect of the invention, a method is provided of treating a material with the polymer of the first aspect of the invention. Preferably the material is treated in an aqueous solution.

Durability of the polymers may be further improved by the addition of polyhydric alcohols.

The invention will now be described, by way of non-limiting example, with reference to figures 1 which shows the reaction scheme during the production of a polymer used in a particular embodiment of the invention. Although the following example relates to the treatment of fabrics to improve their oil and water repellent properties, this should not be seen as limiting. The invention may be used in other situations where treatment of material with a polymer may improve physical properties eg. abrasion resistance or fire retardance.

EXPERIMENTAL

Referring to figure 1, a solution of 1250 parts surfactant FC 126 (available from Fluorochem Ltd.) in 60000 parts distilled water was added to a stirred solution containing 1050 parts 2,4-dichloro-6-(N-(2-acrylyl)ethylamino)-s-triazine 1, 22500 parts 2-(N-ethylperfluorooctylsulphonamide)ethyl acrylate 2, and 125 parts octanethiol ($C_8H_{17}SH$) in acetone. The mixture was deaerated with argon and then warmed to 55°C before addition of 125 parts potassium persulphate. The temperature was increased to 65°C and stirring maintained under a blanket of argon for 20 hours. The resulting dispersion of polymer 3 was allowed to cool, filtered and stored (total solids content = 20%).

Treatment of Cotton Fabrics using Formulation of Polymer 3.

Sample A: The formulation of polymer 3 obtained from the above experimental procedure was diluted to 30g/litre with a 7.5% w/v sodium carbonate solution. The cotton fabric was immersed in this solution, pad mangled to a 150% wet pick-up, and cured at 150°C for 10 minutes.

Sample B: Cotton fabric was treated in an identical manner to that described for sample A, except that the polymer formulation was diluted with distilled water rather than sodium carbonate solution.

Prior to repellency tests and laundering, the cloth samples were washed with detergent (Tepol, TM) and rinsed with water. Repellency rating are in accordance with AATCC Test Method 118 - 1978, (see AATCC Technical Manual 55, p242 (1979)).

Tables 1 and 2 show the results of oil (O) and water (W) repellancy tests carried out on samples A and B.

Table 1.

	Sample A	Sample B
Initial	O5 W5	O5 W5
5hr Soxhlet with trichloroethylene	O5 W5	O2 W4
3hr Soxhlet with benzotrifluoride	O4 W4	O3 W3

Table 2.

	Sample A	Sample B
Initial	O5 W5	O5 W5
10min boil	O5 W5	O2 W3
10min boil	O5 W5	W
20min boil	O4 W4	W
45min boil	O4 W4	










Tables 1 and 2 show that a more durable oil and water repellent finish results when base is included in the formulation. This is consistent with reaction between cellulosate anions in the cotton (formed by reaction of hydroxyl groups with the base) and the fibre reactive groupings on the polymer.

Claims


1. A polymer for the treatment of materials, characterised by a plurality of side groups of general formula -A-Az, where:

A = (CH₂)_n, wherein non adjacent CH₂ groups may be replaced by O, CO₂, OCO, OCO₂, or phenylene and n may have any integral value from 0 to 16;

and Az is selected from:



and




where X_1, X_2 etc are independently selected from halogen, -NHR, -SO₂CH₃, Alkyl, Aryl, -O-Alkyl or -O-Aryl and at least one of X_1, X_2 etc per group Az is halogen;

$Y = -NH-, -NR- (R=Alkyl), -NHCO-, -O-,$ or $-S-$ and

$Z = -SO_2NH-$ or $-SO_2-$


2. The polymer of claim 1 and further containing fluorine bearing side groups.

3. The polymer of claim 2, containing side groups bearing R_f where:



4. The polymer of claim 3, containing the side group -CO₂ R_f .

5. The polymer of claim 4 having the repeat unit:





6. A material characterised by treatment with a polymer as described in claim 1.

7. A method of treating a material characterised by the use of an aqueous formulation of the polymer described in claim 1.

1/1

Fig.1.



INTERNATIONAL SEARCH REPORT

Intern al Application No
PCT/GB 96/02220

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 D06M14/00 D06M14/02 D06M14/08 D06M14/16 D06M23/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 D06M B05D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P,Y	GB 2 291 439 A (SECR DEFENCE) 24 January 1996 see the whole document	1-7
Y	US 4 507 324 A (OLIVE SALVADOR ET AL) 26 March 1985 see the whole document	1-7
Y	WO 92 18332 A (PEACH STATE LABS INC) 29 October 1992 see the whole document	1-7
A	US 4 032 495 A (PERRONIN JEAN ET AL) 28 June 1977 see the whole document	1-7
A	EP 0 221 046 A (MONSANTO CO) 6 May 1987 -/-	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

14 February 1997

Date of mailing of the international search report

24.02.97

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+31-70) 340-3016

Authorized officer

Blas, V

INTERNATIONAL SEARCH REPORT

Intern al Application No
PCT/GB 96/02220

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p>WO 95 24976 A (DOW CHEMICAL CO) 21 September 1995</p> <p>-----</p>	

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/GB 96/02220

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
GB-A-2291439	24-01-96	GB-A- 2291655	31-01-96
US-A-4507324	26-03-85	EP-A- 0161382 JP-A- 60199976	21-11-85 09-10-85
WO-A-9218332	29-10-92	US-A- 5316850 AU-A- 1872792 CA-A- 2107776 EP-A- 0582687 JP-T- 6510337	31-05-94 17-11-92 29-10-92 16-02-94 17-11-94
US-A-4032495	28-06-77	FR-A- 2175332 BE-A- 796578 CA-A- 1012668 CH-B- 571100 CH-A- 340673 DE-A- 2311784 GB-A- 1433524 JP-C- 1085083 JP-A- 48102788 JP-B- 56025945 NL-A, B, C 7303244	19-10-73 10-09-73 21-06-77 31-12-75 15-05-75 13-09-73 28-04-76 25-02-82 24-12-73 16-06-81 12-09-73
EP-A-0221046	06-05-87	US-A- 4794002 AU-B- 589701 AU-A- 6461786 CA-A- 1283582 DE-A- 3683127 JP-B- 7014469 JP-A- 62176508 US-A- 5139881	27-12-88 19-10-89 07-05-87 30-04-91 06-02-92 22-02-95 03-08-87 18-08-92
WO-A-9524976	21-09-95	AU-A- 2101295 CA-A- 2185554 EP-A- 0750531 NO-A- 963862	03-10-95 21-09-95 02-01-97 13-11-96